



Terephthalic Acid based Sheet Moulding Compound (SMC) Resin

Polyseal -100 SP

General Information

POLYSEAL -100 SP is a thickenable, medium viscous and medium reactive Terephthalic acid based SMC grade polyester resin.

Typical Liquid Resin

Properties

<u>Properties</u>	<u>Specified Range</u>	<u>Unit</u>
Acid Value	20-28	mg KOH/gm of Resin
Viscosity @ 25°C Brookfield Viscometer RVDV1-M , Spindle 2, RPM- 20.	800-1100	cps
Monomer Content	30-34	%
Gel Time @ 82°C With 2% BPO Paste	5-6	Min
Peak Exotherm Temperature	Minimum 200	°C
Peak Time	3-4	Min
Gel Time @ 140°C With 1.3% TBPB Paste	4-5	Min
Peak Exotherm Temperature	Minimum 225	°C
Peak Time	Max. 2	Min
Specific Gravity @25°C	1.1-1.2	Gm/cc

Properties are tested in controlled laboratory condition, according to the method described in **IS 6746-1994**.

All the physical parameters can be tailored for suitability of customer's specific end application.

Strongbonds Polyseal Pvt. Ltd.

An ISO 9001 : 2015 Company

CIN No: U51909WB1990PTC049585

Website: www.strongbondspolyseal.com

P-26 C ; Block – D ; Kalyani Industrial Estate

Nadia:741235 ; West Bengal ; India

Tel : 033 2582 3061

Email: strongbondpolyseal@gmail.com

City Office:

CD- 82, Salt Lake City,

Sector-I, Kolkata- 700064

Tel : 033 2334-8136



Mechanical Properties of Cured Resin

<u>Properties</u>	<u>Unit</u>	<u>Nominal Values</u>	<u>Test Method</u>
Tensile Strength	MPa	65	ISO 527-4
Elongation at break	%	2-3	-
Flexural Strength	MPa	86	ISO 178
Heat Deflection Temp.	°C	100	ISO 75
Barcol Hardness	Barcol	40	ASTM D2583
Volume Shrinkage	%	8-9	-

(Cured for 24 hours at room temperature followed by 12 hrs at 65°C)

Features and Applications

SMC Components manufactured from POLYSEAL – 100 SP exhibit excellent mechanical strength along with electrical insulation, hydrolytic stability, excellent surface finish and higher heat deflection temperature compare to the Orthophthalic SMC resins.

It shows uniform thickening behavior with MgO with fast wetting out of reinforcement. SMC grade resins are mainly used in hot press moulding method using catalyst like TBPB (Tertiary butyl per benzoate), BPO (Di-Benzoyl peroxide) etc.

It has a wide application area in automobile, building, construction sectors and railways. Due to its insulation capacity SMC composites are now chosen to manufacture of electrical & electronic equipments.

Approvals & Certificates

The manufacturing, quality control and distribution of the product by Strongbonds Polyseal Pvt. Ltd. are complying with **ISO 9001: 2015** standard.

Storage & Handling

Like other polyester resins Polyseal -100 SP is sensitive to **temperature, moisture** and **Sun light**. Hence resin containers should be stored at dry places in closed-sealed condition bellow 25°C to ensure optimum resin properties. Prolong exposure to open environment can affect liquid resin properties like viscosity and gel time.

Strongbonds Polyseal Pvt. Ltd.

An ISO 9001 : 2015 Company
CIN No: U51909WB1990PTC049585
Website: www.strongbondspolyseal.com

P-26 C ; Block – D ; Kalyani Industrial Estate
Nadia:741235 ; West Bengal ; India
Tel : 033 2582 3061
Email: strongbondpolyseal@gmail.com

City Office:

CD- 82, Salt Lake City,
Sector-I, Kolkata- 700064
Tel : 033 2334-8136



strongbonds
polyseal

Technical Datasheet

Shelf Life

All the unsaturated polyester resins are of limited shelf life. Under above mentioned conditions the shelf life of the material is 90 days (3 months). Storage at higher temperature will adversely affect resin properties and shelf life.

Packaging

Polyseal – 100 SP is supplied in 25 kg and 35 kg Jarricanes and M.S. Drums containing 225.0 Kg of resin.

Safety Information

Skin contact and vapour inhalation should be avoided during working due to presence of styrene monomer. Wear breathing mask, safety goggles, gloves and protective clothing while working. Please consult Material Safety Datasheet prior to working.

Revision Date: 08.10.2018

N.B. : All the above information is based on the results of tests carried out at our laboratory. All the information indicates general characteristics of the product.

Strongbonds Polyseal Pvt. Ltd.

An ISO 9001 : 2015 Company

CIN No: U51909WB1990PTC049585

Website: www.strongbondspolyseal.com

P-26 C ; Block – D ; Kalyani Industrial Estate

Nadia:741235 ; West Bengal ; India

Tel : 033 2582 3061

Email: strongbondpolyseal@gmail.com

City Office:

CD- 82, Salt Lake City,

Sector-I, Kolkata- 700064

Tel : 033 2334-8136